

In the Claims

Claims Listing:

1. (Currently Amended) A multi-component, longitudinally continuous extrusion suitable for use in the fenestration, decking and remodeling industries, comprising:

a first, high density composite member consisting of a thermoplastic component and a cellulosic fiber component all of a first pre-selected formulation extruded from a primary extruder into an extrusion die, wherein the first member has inner and outer sidewalls defining a high density, thin wall extrusion having at least one enclosed, hollow interior compartment; and ,

a second, low density foamed member consisting of a foamed thermoplastic polymer having a second preselected formulation different from the first pre-selected formulation, coextruded with the first member in a molten state from a secondary extruder into the extrusion die so as to be laterally coextensive with and molecularly bonded to one of the sidewalls of the first member.

2. (Original) The multi-component, longitudinally continuous extrusion of Claim 1, wherein the thermoplastic component of the first high density member has polyvinyl chloride as a principle component by weight.

3. (Currently Amended) The multi-component, longitudinally continuous extrusion of Claim 1, wherein the foamed thermoplastic component of the second member has a ~~substantial~~ cellulosic fiber content.

4. (Original) The multi-component, longitudinally continuous extrusion of Claim 3, wherein the foamed thermoplastic component has polyvinyl chloride as a principle component by weight.

5. (Original) The multi-component, longitudinally continuous extrusion of Claim 3, wherein the foamed thermoplastic component has styrene acrylonitrile as a principle component by weight.

6. (Original) The multi-component, longitudinally continuous extrusion of Claim 1, wherein the second member is laterally adjacent to, and longitudinally coextensive with the inner sidewall of the first high density member.

7. (Currently Amended) ~~A~~ The multi-component, longitudinally continuous extrusion of Claim 1 suitable for use in the fenestration, decking and remodeling industries, comprising:

a first, high density composite member consisting of a thermoplastic component and a cellulosic fiber component all of a pre-selected formulation extruded from a primary extruder into an extrusion die, wherein the first member has inner and outer sidewalls defining a high density, thin wall extrusion having at least one enclosed, hollow interior compartment; and

wherein the a second, low density foamed member consisting of a foamed thermoplastic polymer having a second pre-selected formulation different from the first pre-selected formulation, coextruded with the first member in a molten state from a secondary extruder into the extrusion die so as to be molecularly bonded to, is laterally adjacent to and longitudinally coextensive with the outer sidewall of the first high density member.

8. (Currently Amended) ~~The~~ A multi-component, longitudinally continuous extrusion of Claim 1 suitable for use in the fenestration, decking and remodeling industries, comprising:

a first, high density composite member consisting of a thermoplastic component and a cellulosic fiber component all of a pre-selected formulation extruded from a primary extruder into an extrusion die, wherein the first member has inner and outer sidewalls defining a high density, thin wall extrusion having at least one enclosed, hollow interior compartment; and

a wherein the second, low density foamed member is consisting of a foamed thermoplastic polymer having a second pre-selected formulation different from the first pre-selected formulation, coextruded with the first member in a molten state from a secondary extruder into the extrusion die so as to be molecularly bonded to, laterally adjacent to and longitudinally coextensive with both the inner and outer sidewalls of the first high density member.

9. (Original) The multi-component, longitudinally continuous extrusion of Claim 1, including a third member consisting of a thermoplastic cap laterally adjacent to and coextensive with a laterally outermost one of the first and second members of the multi-component extrusion, wherein the thermoplastic cap is coextruded from a tertiary extruder into the extrusion die substantially simultaneously with the first and second members so as to be molecularly bonded with the laterally outermost member.

10. (Currently Amended) The multi-component, longitudinally continuous extrusion of Claim 9, wherein the extrusion defines left hand and right hand sides, and wherein the thermoplastic cap has a ~~highly~~-weatherable thermoplastic polymer on the left hand side and a ~~highly~~-paintable thermoplastic polymer on the right hand side.

11. (Currently Amended) ~~A~~ ~~The~~ multi-component, longitudinally continuous extrusion of Claim 10 suitable for use in the fenestration, decking and remodeling industries, comprising:

a first, high density composite member consisting of a thermoplastic component and a cellulosic fiber component all of a first pre-selected formulation extruded from a primary extruder into an extrusion die, wherein the first member has inner and outer sidewalls defining a high density, thin wall extrusion having at least one enclosed, hollow interior compartment; and,

a second, low density foamed member consisting of a foamed thermoplastic polymer having a second preselected formulation different from the first pre-selected formulation, coextruded with the first member in a molten state from a secondary extruder into the extrusion die so as to be laterally coextensive with and molecularly bonded to one of the sidewalls of the first member; and,

a third member consisting of a thermoplastic cap laterally adjacent to and coextensive with a laterally outermost one of the first and second members of the multi-component extrusion, wherein the thermoplastic cap is coextruded from a tertiary extruder into the extrusion die substantially simultaneously with the first and second members so as to be molecularly bonded with the laterally outermost member wherein the extrusion defines left hand and right hand sides, and wherein the thermoplastic cap has a ~~highly~~-weatherable thermoplastic polymer on the left hand side with ~~has~~-polyvinyl chloride as a principle component by weight, and a ~~wherein the highly~~-paintable thermoplastic polymer on the right hand side with ~~has~~-acrylic styrene acrylonitrile (ASA) as a principle component by weight.

12. (Withdrawn) A multi-plate extrusion die of the type having a plurality of die plates sequentially positioned so as to define upstream and downstream directions, comprising:

an introductory plate generally defining a primary aperture for passage therethrough of a primary extrudate, the primary aperture extending longitudinally through substantially each die plate of the extrusion die;

a mandrel plate downstream of the introductory plate and fluidly connected thereto for receipt of the primary extrudate and a secondary extrudate, having a first elongated mandrel substantially suspended therein by first support means for supporting the first mandrel in a spaced apart relationship within the primary aperture, wherein the first mandrel is substantially hollow and has a second mandrel substantially suspended therein by second means for supporting the second mandrel in a spaced apart relationship within the first mandrel so as to form an elongated hollow, interstitial void between the first and second mandrels; and,

a secondary plate positioned between the introductory and mandrel plates having means for introducing the second extrudate into the interstitial void, whereby an elongated final extrudate having at least two different longitudinally continuous, molecularly bonded thermoplastic components can exit the mandrel plate.

13. (Withdrawn) The multi-plate extrusion die of Claim 12, including a capstock plate, positioned downstream of the mandrel plate, for adding a third extrudate in the form of a capstock to the final extrudate.

14. (Withdrawn) The multi-plate extrusion die of Claim 12, wherein the first and second support means are elongated tapered fins having a decreasing thickness from the upstream direction to the downstream direction.

15. (Withdrawn) A method of making a multi-component, longitudinally continuous extrusion suitable for use in the fenestration, decking and remodeling industries with a multi-plate extrusion die of the type having a plurality of die plates sequentially positioned so as to define upstream and downstream directions, comprising the steps of:

preparing a thermoplastic primary extrudate and a thermoplastic secondary extrudate;

introducing the primary extrudate in a molten state into an introductory plate generally defining a primary aperture for passage therethrough of the primary extrudate, wherein the primary aperture extends longitudinally through substantially each die plate of the extrusion die;

positioning a mandrel plate downstream of and fluidly connected to the introductory plate, wherein the mandrel plate has a first elongated mandrel suspended in a spaced apart relationship within the primary aperture and wherein the first mandrel is substantially hollow and has a second mandrel substantially suspended therein in a spaced apart

relationship within the first mandrel so as to form an elongated, hollow, interstitial void between the first and second mandrels; and,

introducing the secondary extrudate in a molten state into the interstitial void, whereby an elongated final extrudate having at least two different longitudinally continuous, molecularly bonded thermoplastic components exit the mandrel plate.

16. (Withdrawn) The method of Claim 15, wherein the first extrudate is prepared so as to substantially consist of a thermoplastic component and a cellulosic fiber component, and wherein the second extrudate is prepared so as to substantially consist of a foamed thermoplastic polymer.

17. (Withdrawn) The method of Claim 16, wherein the second extrudate includes a substantial cellulosic component.

18. (Withdrawn) The method of Claim 15, including the step of providing a third thermoplastic capstock extrudate, positioning a capstock plate downstream of the mandrel plate, introducing the third extrudate in a molten state to an exterior surface of the final extrudate so as to form a cap.

19. (Withdrawn) The method of Claim 18, wherein the final extrudate defines left hand and right hand sides, including the steps of simultaneously applying two different types of thermoplastic capstocks to the final extrusion, one of the thermoplastic capstock materials consisting of a highly weatherable thermoplastic polymer on the left hand side and another of the thermoplastic capstock materials consisting of a highly paintable thermoplastic polymer on the right hand side.